



# Firebrake® 500



Anhydrous Zinc Borate

Hexaboron Dizinc Undecaoxide

CAS Number 12767-90-7

*Firebrake*® 500 is a dehydrated zinc borate with multifunctional fire retardant applications in a variety of polymers. Since it contains no water of hydration, it is stable up to 600°C. It can therefore be used in polymer systems requiring very high processing temperatures. It can be fed to extruders, calenders, or injection moulding equipment in the same way as other solid polymer additives.

## Applications

*Firebrake* 500 can be used as a flame retardant and smoke suppressant in a variety of polymers including polyetherketone, polysulfone, fluoropolymer, polyester, and nylon. The very significant beneficial effect of *Firebrake* 500 on the rate of heat release is of special interest where this factor is important, as in aircraft applications.

## Storage

*Firebrake* 500 should be stored in a sealed container because of its tendency to gradually pick up surface moisture in high humidity environments. This surface moisture is easily removed by heating at about 200°C. The product is chemically stable and shows little tendency to cake.

\*Protected by US and international patents.

## Chemical and physical properties

Typical properties	
Refractive index	1.58
Median particle size (laser diffraction)	9 microns
Weight loss (TGA)	1.5% max. to 400°C
Thermal stability	Stable up to about 600°C. Can gradually absorb surface moisture—store in sealed container
Specific gravity	2.6

Theoretical chemical composition	
Boric oxide (B <sub>2</sub> O <sub>3</sub> ), %	56.2
Zinc oxide (ZnO), %	43.8



**Notice:** Before using these products, please read the Product Specifications, the Safety Data Sheets and any other applicable product literature. The descriptions of potential uses for these products are provided only by way of example. The products are not intended or recommended for any unlawful or prohibited use including, without limitation, any use that would constitute infringement of any applicable patents. Nor is it intended or recommended that the products be used for any described purposes without verification by the user of the products' safety and efficacy for such purposes, as well as ensuring compliance with all applicable laws, regulations and registration requirements. Suggestions for use of these products are based on data believed to be reliable. The seller shall have no liability resulting from misuse of the products and provides no guarantee, whether expressed or implied, as to the results obtained if the products are not used in accordance with directions or safe practices. The buyer assumes all responsibility, including any injury or damage, resulting from misuse of the product, whether used alone or in combination with other materials. THE SELLER MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THE SELLER SHALL HAVE NO LIABILITY FOR CONSEQUENTIAL DAMAGES.

