



Firebrake® ZB



Zinc Borate

Hexaboron Dizinc Undecaoxide, Hydrate

Firebrake® ZB

Firebrake® ZB Fine

Firebrake® ZB-XF

CAS Number 138265-88-00

Firebrake® ZB is a unique form of zinc borate with multi-functional fire retardant applications in plastic and rubber compounds. Since *Firebrake* ZB releases its water of hydration at temperatures exceeding 290°C (554°F), it can be used in systems requiring high processing temperatures. *Firebrake* ZB has a refractive index similar to that of most polymer systems, which results in the retention of considerable translucency and allows the use of low pigment loading. It can be fed to extruders, calenders, or injection molding equipment in much the same way as other solid polymer additives.

Applications

Firebrake ZB is used as a flame retardant, smoke and afterglow suppressant, and anti-arcing agent in polymer systems such as polyvinyl chloride, nylon, epoxy, polyethylene, polypropylene, polyesters, thermoplastic elastomers and rubbers.

Depending on the base polymer used and fire standards to be met, *Firebrake* ZB can be used to replace partially (or even completely) other fire retardant additives such as antimony oxide. In some

systems, *Firebrake* ZB displays synergism with antimony oxide. In halogen-containing systems, the usage level of *Firebrake* ZB is in the range of 3-25 parts per 100 parts of resin (phr). In halogen-free systems, the recommended level is in the range of 10-25 phr, normally used in conjunction with alumina trihydrate, magnesium hydroxide, or a silicone polymer. In some cases, our technical team may be able to give recommendations for starting point formulations.

Firebrake ZB Fine and *Firebrake* ZB-XF are recommended for applications where maximum fire test performance is needed, and physical properties such as film forming and adhesion are critical. The XF grade has no particles greater than 12 microns, as determined by laser diffraction technique, and therefore is suitable for more critical applications.

Storage

When stored under normal conditions of temperature and humidity, *Firebrake* ZB products are chemically stable and show little tendency to cake.

Firebrake® ZB

Chemical and physical properties

Typical properties	
Refractive index	1.58
Median particle size <i>Firebrake ZB</i> <i>Firebrake ZB-Fine</i> <i>Firebrake ZB-XF</i>	(Laser diffraction) 9 microns 2.1 microns 1.8 microns
Solubility	Less than 0.28% in water at room temp.
Thermal stability	Stable up to 290°C. Can be hydrolyzed by strong acids and bases.
Specific gravity	2.77

Theoretical chemical composition	
Boric oxide (B ₂ O ₃), %	48.05
Zinc oxide (ZnO), %	37.44
Water (H ₂ O), %	14.51
Anhydrous equivalent, 2ZnO B ₂ O ₃ , %	85.49



Notice: Before using these products, please read the Product Specifications, the Safety Data Sheets and any other applicable product literature. The descriptions of potential uses for these products are provided only by way of example. The products are not intended or recommended for any unlawful or prohibited use including, without limitation, any use that would constitute infringement of any applicable patents. Nor is it intended or recommended that the products be used for any described purposes without verification by the user of the products' safety and efficacy for such purposes, as well as ensuring compliance with all applicable laws, regulations and registration requirements. Suggestions for use of these products are based on data believed to be reliable. The seller shall have no liability resulting from misuse of the products and provides no guarantee, whether expressed or implied, as to the results obtained if the products are not used in accordance with directions or safe practices. The buyer assumes all responsibility, including any injury or damage, resulting from misuse of the product, whether used alone or in combination with other materials. THE SELLER MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THE SELLER SHALL HAVE NO LIABILITY FOR CONSEQUENTIAL DAMAGES.